



REPORT NUMBER: 3109888-R1
ORIGINAL ISSUE DATE: January 30, 2007
REVISED DATE: January 31, 2007

EVALUATION CENTER
Intertek Testing Services NA Ltd.
1500 Brigantine Drive
Coquitlam, BC V3K 7C1

RENDERED TO

LOGIX INSULATED CONCRETE FORMS LTD.
SUITE 327, 801 KLAHANIE DRIVE
PORT MOODY, BC V3H 5K4

PRODUCT EVALUATED: Logix ICFs
EVALUATION PROPERTY: ASTM E96

Engineering Evaluation of Logix ICF for compliance with the applicable requirements of the following criteria: ASTM E96/96M-05, Standard Test Methods for Water Vapor Transmission of Materials and 2005 National Building Code

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to copy or distribute this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

1 Introduction

Intertek Testing Services NA Ltd. (Intertek) has conducted an engineering evaluation for Logix Insulated Concrete Forms Ltd., on Logix ICF, to evaluate the vapor permeance properties of the product. The evaluation was conducted to determine if Logix ICF meets the 2005 National Building Code (NBC) for use as a vapor barrier.

2 Sample Description

Logix ICF consists of rigid interlocking expanded polystyrene (EPS) foam plastic boards that serve as permanent formwork for reinforced concrete, exterior and interior walls, and foundation and retaining walls.

3 Reference Documents

- 2005 National Building Code (NBC)
- ASTM E96/96M-05, Standard Test Methods for Water Vapor Transmission of Materials (ASTM E96)
- Intertek Test Report 3048347 dated October 14, 2003
- Intertek Letter dated January 6, 2005

4 Evaluation Method

Vapor barrier properties and installation are described in detail in Section 5.5.1.2 of the 2005 NBC. These details are summarized below:

- 1) The vapor barrier shall have sufficiently low permeance and shall be positioned in the building component or assembly so as to
 - a) minimize moisture transfer by diffusion, to surfaces within the assembly that would be cold enough to cause condensation at the design temperature and humidity conditions, or
 - b) reduce moisture transfer by diffusion, to surfaces within the assembly that would be cold enough to cause condensation at the design temperature and humidity conditions, to a rate that will not allow sufficient accumulation of moisture to cause deterioration or otherwise adversely affect any of
 - i. the health or safety of building users,
 - ii. the intended use of the building, or
 - iii. the operation of building services.
- 2) Coatings applied to gypsum wallboard to provide required resistance to vapour diffusion shall conform to the requirements of Sentence (1) when tested in accordance with CAN/CGSB-1.501-M, "Method for Permeance of Coated Wallboard."

- 3) Coatings applied to materials other than gypsum wallboard to provide required resistance to vapor diffusion shall conform to the requirements of Sentence (1) when tested in accordance with ASTM E96, "Water Vapor Transmission of Materials" by the desiccant method (dry cup).

Vapor Barrier materials are further discussed in Section 9.25.4.2 of the 2005 NBC under Sentence (1) which is summarized below:

- 1) Vapor barriers shall have a permeance not greater than 60 ng/Pa-s-m² measured in accordance with ASTM E96, "Water Vapor Transmission of Materials" by the desiccant method (dry cup).


Logix ICF fall under Sentence (3) of Section 5.5.1.2 of the 2005 NBC and have been tested by Intertek in accordance with ASTM E96 using the desiccant method. The results were summarized in Intertek Test Report 3048347 dated October 14, 2003 and showed that a 1-inch Logix ICF had a water permeance of 100 ng/Pa-s-m². In the field, Logix ICF is installed with a 2.75-inch thickness and thus the calculated water permeance at this thickness is 36 ng/Pa-s-m². The detailed calculations are shown in Intertek Letter dated January 5, 2005. Based on these results, Logix ICF meets the requirements of Section 9.25.4.2, Sentence (1) of the 2005 NBC and can be installed without the use of a vapor barrier.

5 Conclusion

Intertek has conducted an engineering evaluation for Logix Insulated Concrete Forms Ltd., on Logix ICF, to determine if the Logix ICF meets the 2005 National Building Code as a vapor barrier. The analysis, per Section 4 above, showed that Logix ICF meets the water permeance requirements and can be installed without a vapor barrier.

INTERTEK TESTING SERVICES NA LTD.

Reported by: 
Matt Lansdowne, EIT
Engineer, Building Products

Reviewed by: 
Kal Kooner, EIT
Team Leader, Engineering Services Canada

REVISION SUMMARY

| DATE | SUMMARY |
|------------------|---|
| February 1, 2007 | Added additional reference to 2005 NBC and maximum permeance requirements |
| | |
| | |