

LOGIX® INSULATED CONCRETE FORMS

All documents are downloadable at logixcf.com

8.5 – LOGIX R-VALUES

LOGIX FORM PANELS	STANDARD		TAPER TOP		BRICK LEDGE	
STANDARD						
	LOGIX	LOGIX PLATINUM	LOGIX	LOGIX PLATINUM	LOGIX	LOGIX PLATINUM
R1/R2 (RSI) ¹	23/24 (4/4.25)	26/27 (4.56/4.81)	23/24 (4/4.25)	26/27 (4.56/4.81)	23/24 (4/4.25)	26/27 (4.56/4.81)
TAPER TOP						
			LOGIX	LOGIX PLATINUM	LOGIX	LOGIX PLATINUM
R1/R2 (RSI) ¹			23/24 (4/4.25)	26/27 (4.56/4.81)	23/24 (4/4.25)	26/27 (4.56/4.81)
BRICK LEDGE						
					LOGIX	LOGIX PLATINUM
R1/R2 (RSI) ¹					23/24 (4/4.25)	26/27 (4.56/4.81)

1. R1 denotes total R-value of form panels only (per ASTM C518 at average mean temperature of 75deg F.). R2 denotes total R-value of a wall assembly consisting of form panels, 4 inch concrete core, 1/2 inch drywall and interior airfilm. R1 and R2 are based on imperial units. R-values are based on independent testing conducted by Intertek Testing Services.

SPECIFICATIONS & REFERENCES