

---

## LOGIX INSULATED CONCRETE FORMS MATERIAL PROPERTY DATA SHEET

This document is intended for general information purposes only regarding specifications for Logix Insulated Concrete Forms, *excluding Logix XP-1 products*, (herein referred to as Logix ICF). Technical specification sheet, as per Construction Specifications institute (CSI) formatting, can be downloaded at [www.logixicf.com](http://www.logixicf.com).

### 1 PRODUCT DESCRIPTION

- Logix ICF consists of two flame-resistant EPS boards separated by polypropylene webs.
- Logix ICF consists of solid form units (LOGIX Pro Forms) or knock-down forms (LOGIX KD Forms) or a combination of both Logix form and Logix KD forms, referred to as LOGIX Hybrid Forms.
- The EPS foam boards are a minimum 70 mm (2.75 inch) thick. Increased EPS foam boards are available by utilizing D-Rv insert panels, which provides additional thickness in increments of 50 mm (2 inch).
- The webs separate the EPS boards to form 102 mm (4 inch), 159 mm (6.25 inc), 203 mm (8 inch), 254 mm (10 inch) and 305 mm (12 inch) cavities, which create the concrete wall thicknesses. With Logix Xtenders the concrete wall thickness can be increased to virtually any thickness.
- The webs are spaced every 203 mm (8 inch) on centre horizontally and 406 mm (16 inch) on centre vertically, and contain a 32 mm (1.25 inch) wide furring strip that extends the height of each ICF block. The furring strips shall facilitate fasteners for attachment of both exterior and interior finishes.
- A furring strip is located in the corners of corner forms. The furring strip consists of both a vertical and horizontal component. The vertical component extends nearly the full height of the form, extends a minimum of 64 mm (2.5 inches) from both sides of the corner, and a minimum of 5 mm (0.2 inches) thick. The horizontal component is a minimum 51mm (2 inches) in height, extend a minimum of 152 mm (6 inches) from both sides of the corner, and a minimum of 5 mm (0.2 inches) thick.
- The webs facilitate rebar placement in accordance with CAN/CSA A23.1, and ACI 318

## 2 LOGIX PRODUCTS

Logix manufactures both assembled and unassembled insulated concrete form units. Logix assembled forms, known simply as “Logix PRO”, are delivered to the job site as assembled form blocks. Logix unassembled forms (or knock-down forms), known as “Logix KD”, are delivered to the job site in components that make up the form blocks - the form panels and KD Connectors. Logix KD are assembled on the job site.

Below is a summary of the types of Logix and Logix KD forms available.

### LOGIX (assembled form blocks)

	Description
<b>Logix Pro</b>	White in color
<b>Logix Pro Platinum<sup>3</sup></b>	Grey in color. Offers higher R-value <sup>1</sup> than Logix Pro.
<b>Logix Pro TX</b>	Logix Pro with termite resistant additive Preventol <sup>2</sup> .
<b>Logix Pro Platinum<sup>3</sup> TX</b>	Logix Platinum with Preventol.

### LOGIX KD (unassembled form blocks)

	Description
<b>Logix KD</b>	White in color
<b>Logix KD Platinum<sup>3</sup></b>	Grey in color. Offers higher R-value <sup>1</sup> than LOGIX Pro.
<b>Logix KD TX</b>	Logix Pro with termite resistant additive Preventol <sup>2</sup> .
<b>Logix KD Platinum<sup>3</sup> TX</b>	Logix Platinum with Preventol.

Notes:

1. See Logix Design Manual, Section 8.5 for Logix R-values.
2. Preventol is an effective termite resistant additive.
3. Care should be taken to protect exposed foam surfaces from reflected sunlight and prolonged solar exposure until wall cladding or finish material is applied. Shade exposed foam areas, or remove sources of reflective surfaces, where heat buildup onto exposed foam might occur. For more information refer to BASF Technical Leaflet N-4 Neopor, “Recommendations for packaging, transporting, storing and installing building insulation products made from Neopor EPS foam.” (The BASF Technical Leaflet is attached to every bundle of LOGIX Platinum forms delivered to a job site).

## LOGIX INSULATED CONCRETE FORMS GENERAL SPECIFICATIONS SHEET, CONT'D

### 3 CODE/CERTIFICATION APPROVALS

- QAI evaluation to IBC and IRC 2012/2015
- Miami-Dade County Approval No.19-0925.02
- State of Florida Certification of Approval No.FL14469-R3
- Wisconsin Building Products Evaluation No.20199000
- City of New York Materials and Equipment Acceptance – MEA 273-04-M
- QAI listed QM0503
- ASTM E2634, Standard Specification for Flat Wall Insulating Concrete Form (ICF) Systems
- ASTM C578, Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation
- CAN/ULC S717, Standard for Flat Wall Insulating Concrete Form (ICF) Units - Material Properties
- CAN/ULC S701, Standard for Thermal Insulation, Polystyrene Boards

### 4 DESIGN/PERFORMANCE OF LOGIX ICF

A brief description of each test is outlined in the attached Appendix. Test reports are available upon request.

Test Description	Result	Pass/Fail Criteria	Referenced Standard Test Method
R-Value (Thermal Resistance) per inch (per 25.4mm)	R 4.13 (RSI 0.72)	Min. R 4.00 (RSI 0.70)	ASTM C518
Water Absorption	0.18%	Max. 3.0%	ASTM D2842
Water Vapor Presence	100.0ng/Pa-s-m2 (1.74perm-in.)	Max. 201 ng/Pa-s-m2 (3.5perm-in.)	ASTM E96
Compressive Strength	165kPa (23.9psi)	Min. 104kPa (15.0psi)	ASTM D1621 & ASTM C165
Flexural Strength	365kPa (53.0psi)	Min. 240kPa (35.0psi)	ASTM C203
Dimensional Stability – Thermal & Humid Aging	0.5%	Max. 2.0%	ASTM D2126
Density	27.5kg/m3 (1.72pcf)	Min. 22 kg/m3 (1.35pcf)	ASTM C1622 & ASTM C303
Dimensions	Min. length variation = 0.0% Max. length variation = 0.4% Min. width variation = 0.1% Max. width variation = 0.4% Min. thickness variation = -0.3mm Max. thickness variation = 0.9mm Max. squareness = 3mm	Min. -0.2% Max. 0.4% Min. -0.2% Max. 0.4% Max. -2mm Max. 4mm Max. 3mm	ASTM C303
Limiting Oxygen Index	29.1%	Min. 24.0%	ASTM D2863
Formaldehyde Emission	No formaldehyde detected	N/A*	AATTC-112
Fungi Resistance	No fungal growth detected	N/A*	ASTM G21
Flame Spread Rating	≤ 75 / ≤ 210	N/A*	ASTM E84/CAN ULC S102

LOGIX INSULATED CONCRETE FORMS  
GENERAL SPECIFICATIONS SHEET, CONT'D

Test Description	Result	Pass/Fail Criteria	Referenced Standard Test Method
Smoke Developed Rating	≤ 450 / ≥ 500	N/A*	ASTM E84/CAN ULC S102
Fire Endurance Test	See Fire Resistance Rating table	N/A*	ASTM E119/CAN ULC S101
Standard Room Fire Test	w/in acceptable limits	Met conditions required for exposure to fire for 15 minutes.	UBC 26-3/CAN ULC 1715
Concrete Pour-in-place	Observations of deflection recorded.	N/A*	CCMC Masterformat 03131
Sound Transmission	STC 56 for 6.25" Logix wall system (2 layers of 5/8" drywall & 2x2 wood strips on one side, 1/2" drywall on the other side) STC 50 for 4" Logix wall system (1/2" drywall & 2x2 wood strips on one side, 1/2" drywall on the other side).	N/A*	ASTM E90
UPITT Toxicity	Pass	LC50 < 19.7g	University of Pittsburgh Toxicity Test

\*Code body or referenced test standard required reporting test results only - no Pass/Fail criteria specified.

**LOGIX INSULATED CONCRETE FORMS  
GENERAL SPECIFICATIONS SHEET, CONT'D**

**TESTS CONDUCTED ON POLYPROPYLENE WEB**

Test Description	Result	US Requirements	Referenced Standard Test Method
Flammability	Flame Front Distance = 100mm (4") Avg. Linear Burn Rate = 17.9mm/min (0.70in/min)	Max. linear burn rate = 40.0mm/min (1.57in/min) for Flame Front Dist. = 100mm (4")	ASTM D635
Smoke Density Rating	19.1%	Max. 75%	ASTM D2843
Shear Strength of Polypropylene Web	26.1MPa (37.9psi)	N/A*	ASTM D732, CCMC Masterformat 03131
Average Tensile Strength of Polypropylene Webs (used for Logix Pro ICF blocks).	3.75kN (842lbs)	N/A*	ASTM D638
Average Lateral Fastener Resistance of Drywall Screws	1.63kN (367lbs)	N/A*	ASTM D1761
Average Withdrawal Fastener Resistance of Drywall Screws	0.75kN (169lbs)	N/A*	ASTM D1761
Average Withdrawal Resistance of Staples 1.59mm 16ga.	105N (24lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Withdrawal Resistance of Plane Shank 1.5" long, 3/8" head	155N (35lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Withdrawal Resistance of Ring Shank 1.5" long, 3/8" head	431N (97lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Withdrawal Resistance of Spiral Shank 1.5" long, 3/8" head	135N (30lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Lateral Resistance of Staples 1.59mm 16ga.	169N (38lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Lateral Resistance of Plane Shank 1.5" long, 3/8" head	520N (117lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Lateral Resistance of Ring Shank 1.5" long, 3/8" head	378N (85lbs)	N/A*	ASTM D1761 (under cyclic temperatures)
Average Lateral Resistance of Spiral Shank 1.5" long, 3/8" head	200N (45lbs)	N/A*	ASTM D1761 (under cyclic temperatures)

LOGIX INSULATED CONCRETE FORMS  
GENERAL SPECIFICATIONS SHEET, CONT'D

Test Description	Result	US Requirements	Referenced Standard Test Method
Average Withdrawal Resistance of Corrosion Resistance No.8-18 x 0.323 HD x 1.5/8"	567N (127lbs)	N/A*	ASTM D1761
Average Withdrawal Resistance of Corrosion Resistance 6d (0.113" shank x 0.267 HD x 2" long)	93N (21lbs)	N/A*	ASTM D1761
#6 Coarse Drywall Screw, 1-5/8" long**	787N (177lbs)	N/A*	ASTM D1761
#6 Fine Drywall Screw, 1-5/8" long**	765N (172lbs)	N/A*	ASTM D1761
16ga. Staple, 1-1/2" long**	124N (28lbs)	N/A*	ASTM D1761
Galvanized Ringed Wallboard Nail, 1-1/2" long**	462N (104lbs)	N/A*	ASTM D1761
Hot-dipped Galvanized Spiral Nail, 2" long**	226N (51lbs)	N/A*	ASTM D1761
#8 Wood Screw, 2" long**	920N (207lbs)	N/A*	ASTM D1761
#8 Exterior Deck Screw, 2" long**	934N (210lbs)	N/A*	ASTM D1761
#10 Wood Screw, 2" long**	880N (198lbs)	N/A*	ASTM D1761

\*Code body or referenced test standard required reporting test results only - no Pass/Fail criteria specified.

\*\*Applicable to corner web only.

#### FIRE RESISTANCE RATING

Form Size (Concrete Wall Thickness)	Rating with ½" drywall
100mm (4")	2hrs
159mm (6.25")	3hrs (4hrs if 5/8" drywall used)
203mm (8") and above	4hrs

\*Bearing load applied to wall = 360,000lbs (360kips)